



**American Coal Ash Association (ACAA)
2000 Coal Combustion Product (CCP)
Production and Use (Short Tons)**

Total CCPs - Category I (Dry) & II (Ponded)	Fly Ash	Bottom Ash	Boiler Slag	FGD Material
CCP Production	62,943,732	16,915,826	2,684,889	25,652,994
Subtotal - Fly Ash, Bottom Ash, and Boiler Slag			82,544,446	
Total All CCPs				108,197,440
CCP Use				
Cement/Concrete/Grout	10,586,168	419,832	276	350,928
Raw Feed for Cement Clinker	1,133,911	173,813	0	0
Flowable Fill	696,675	10,958	18,000	33,452
Structural Fills	2,611,054	1,351,390	35,683	547,017
Road Base/Subbase	1,207,750	836,568	13	93,519
Soil Modification	111,896	27,907	0	0
Mineral Filler	119,011	102,063	12,424	984
Snow and Ice Control	3,076	831,708	58,206	0
Blasting Grit/Roofing Granules	0	146,983	2,098,577	0
Mining Applications	1,151,536	366,584	0	182,829
Wallboard	0	0	0	3,328,651
Waste Stabilization/Solidification	1,986,277	35,787	0	21,031
Agriculture	13,979	4,748	0	75,922
Miscellaneous/Other	455,576	629,567	98,389	190,394
Total Use	20,076,909	4,937,908	2,321,568	4,824,727
Subtotal - Fly Ash, Bottom Ash, and Boiler Slag			27,336,385	
Total All CCPs				32,161,112
Individual Use Percentage	31.9%	29.2%	86.5%	18.8%
Cumulative Use Percentage	31.9%	31.3%	33.1%	29.7%

For metric equivalents, multiply tabular values by 0.9078

American Coal Ash Association
6940 South Kings Highway, Suite 207
Alexandria, VA 22310-3344 USA
Phone: 703-317-2400 Fax: 703-317-2409
Internet: <http://www.ACAA-USA.org>